

LVT gluedown only

## Specification



plank



herringbone

|                       |                    |                      |
|-----------------------|--------------------|----------------------|
| Planks per Pack       | 15                 | 40                   |
| Pack Coverage         | 3.41m <sup>2</sup> | 2.116m <sup>2</sup>  |
| Packs per Pallet      | 100                | 140                  |
| Pallet Coverage       | 341m <sup>2</sup>  | 296.24m <sup>2</sup> |
| Plank Dimensions      | 1229 x 185 mm      | 460 x 115 mm         |
| Wear Layer            | 0.30 mm            | 0.30 mm              |
| Thickness             | 2.0 mm             | 2.0 mm               |
| Total Weight per Pack | 13.37 kg           | 8.30 kg              |

## Performance

|                                           |                        |
|-------------------------------------------|------------------------|
| Castor Chair Wheel (EN ISO 4918)          | Pass                   |
| Abrasion Resistance (EN ISO 660-2)        | T Grade                |
| Colour Fastness (EN ISO 105-BO2)          | ≥6                     |
| Fire Rating (BS EN 13501-1)               | B <sub>FL</sub> -s1    |
| Effects of Stain (BS EN 423)              | Pass                   |
| Residual Indentation (BS EN 24343-1)      | ≤ 0.10mm               |
| Dimensional Stability<br>(EN ISO 23999)   | X ≤ 0.15%<br>Y ≤ 0.15% |
| Curling Resultant to Heat (EN ISO 23999)  | ≤ 1.0mm                |
| Chemical Resistance (EN ISO 26987)        | Index 0                |
| Slip Resistance (BS EN 7976)              | 36+ (dry conditions)   |
| Slip Resistance (BS EN 16165 Annex B)     | R10                    |
| Performance Classification (EN ISO 10874) | 23/33/42               |
| Impact Sound Reduction (EN ISO 10140-3)   | 3 dB                   |
| Phthalate Content (EN ISO 14389)          | ≤ 0.01% (Pass)         |
| VOC Emissions (BS EN 16516)               | ND (Pass)              |